

**Phase 1 and 2 West Graham drill Program assay results.**

Hole ID	From (m)	To (m)	Length (m) <sup>1</sup>	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
<b>WG-23-019</b>	64.00	93.00	29.00	0.39	0.25	0.01	0.04	0.02	0.02	1.36	70
<b>WG-23-020</b>	<b>47.00</b>	<b>91.00</b>	<b>44.00</b>	<b>0.53</b>	<b>0.27</b>	<b>0.02</b>	<b>0.05</b>	<b>0.02</b>	<b>0.02</b>	<b>1.41</b>	100
including	75.00	83.00	7.00	0.75	0.39	0.03	0.06	0.02	0.02	1.86	100
including	87.00	91.00	4.00	1.03	0.62	0.04	0.07	0.05	0.03	2.85	100
<b>WG-23-021</b>	<b>41.00</b>	<b>72.00</b>	<b>31.00</b>	<b>0.46</b>	<b>0.29</b>	<b>0.02</b>	<b>0.06</b>	<b>0.02</b>	<b>0.02</b>	<b>1.50</b>	90
including	42.00	46.00	4.00	0.63	0.46	0.02	0.10	0.03	0.04	2.40	90
including	58.00	63.00	5.00	0.66	0.30	0.02	0.04	0.02	0.01	1.50	90
<b>WG-23-022</b>	61.00	81.00	20.00	0.51	0.26	0.02	0.03	0.01	0.01	1.12	100
including	76.00	80.00	4.00	0.85	0.46	0.03	0.05	0.02	0.02	1.80	100
<b>WG-23-023</b>	<b>45.00</b>	<b>83.00</b>	<b>38.00</b>	<b>0.47</b>	<b>0.28</b>	<b>0.02</b>	<b>0.04</b>	<b>0.02</b>	<b>0.02</b>	<b>1.45</b>	90
including	71.00	82.00	11.00	0.71	0.41	0.02	0.07	0.02	0.04	2.09	90
<b>WG-23-024</b>	29.00	48.00	19.00	0.46	0.25	0.02	0.04	0.01	0.02	1.21	100
and	56.00	61.00	5.00	0.93	0.50	0.03	0.06	0.02	0.02	4.18	100
<b>WG-23-025</b>	<b>20.00</b>	<b>67.00</b>	<b>47.00</b>	<b>0.56</b>	<b>0.30</b>	<b>0.02</b>	<b>0.05</b>	<b>0.02</b>	<b>0.02</b>	<b>1.85</b>	90
including	<b>42.00</b>	<b>65.00</b>	<b>23.00</b>	<b>0.72</b>	<b>0.42</b>	<b>0.02</b>	<b>0.08</b>	<b>0.03</b>	<b>0.03</b>	<b>2.73</b>	90
<b>WG-23-026</b>	<b>106.00</b>	<b>186.90</b>	<b>80.90</b>	<b>0.49</b>	<b>0.25</b>	<b>0.02</b>	<b>0.05</b>	<b>0.02</b>	<b>0.02</b>	<b>1.29</b>	35
including	<b>167.00</b>	<b>186.90</b>	<b>19.90</b>	<b>1.19</b>	<b>0.37</b>	<b>0.04</b>	<b>0.09</b>	<b>0.02</b>	<b>0.02</b>	<b>1.29</b>	35
including	<b>170.00</b>	<b>177.90</b>	<b>7.90</b>	<b>2.48</b>	<b>0.64</b>	<b>0.08</b>	<b>0.15</b>	<b>0.04</b>	<b>0.02</b>	<b>1.82</b>	35
<b>WG-23-027</b>	<b>68.00</b>	<b>120.50</b>	<b>52.50</b>	<b>0.43</b>	<b>0.27</b>	<b>0.01</b>	<b>0.05</b>	<b>0.02</b>	<b>0.02</b>	<b>1.49</b>	85
including	<b>96.65</b>	<b>120.50</b>	<b>23.85</b>	<b>0.57</b>	<b>0.33</b>	<b>0.02</b>	<b>0.06</b>	<b>0.02</b>	<b>0.03</b>	<b>1.79</b>	85
including	111.00	120.50	9.50	0.83	0.37	0.02	0.09	0.03	0.03	2.16	85
<b>WG-23-028</b>	<b>79.00</b>	<b>275.85</b>	<b>196.85</b>	<b>0.32</b>	<b>0.19</b>	<b>0.01</b>	<b>0.04</b>	<b>0.01</b>	<b>0.02</b>	<b>1.07</b>	30
including	<b>89.00</b>	<b>110.00</b>	<b>21.00</b>	<b>0.72</b>	<b>0.18</b>	<b>0.03</b>	<b>0.03</b>	<b>0.01</b>	<b>0.01</b>	<b>0.75</b>	30
including	93.60	95.00	1.40	3.73	0.27	0.17	0.06	0.07	0.01	1.26	30
<b>WG-23-029</b>	84.00	107.00	23.00	0.37	0.25	0.01	0.03	0.02	0.02	1.39	50
<b>WG-23-030</b>	<b>20.00</b>	<b>52.00</b>	<b>32.00</b>	<b>0.60</b>	<b>0.36</b>	<b>0.02</b>	<b>0.07</b>	<b>0.02</b>	<b>0.03</b>	<b>2.02</b>	45
including	39.00	46.00	7.00	0.98	0.54	0.03	0.15	0.38	0.04	3.00	45
<b>WG-23-031</b>	3.00	9.65	6.65	0.37	0.22	0.01	0.04	0.01	0.01	1.08	95
<b>WG-23-032</b>	34.50	42.50	8.00	0.49	0.38	0.02	0.05	0.02	0.03	2.00	85
<b>WG-23-033</b>	38.00	52.00	14.00	0.35	0.24	0.01	0.04	0.02	0.02	1.29	80
<b>WG-23-034</b>	59.00	90.00	31.00	0.27	0.19	0.01	0.04	0.01	0.01	1.26	50
including	96.00	97.65	1.65	0.67	0.34	0.02	0.05	0.03	0.03	2.29	50
<b>WG-23-035</b>	43.00	51.00	8.00	0.26	0.21	0.01	0.04	0.02	0.02	1.25	80
<b>WG-23-036</b>	97.00	102.00	5.00	0.39	0.23	0.01	0.05	0.02	0.01	1.54	45
<b>WG-23-037</b>	<b>147.00</b>	<b>188.65</b>	<b>41.65</b>	<b>0.50</b>	<b>0.34</b>	<b>0.02</b>	<b>0.08</b>	<b>0.02</b>	<b>0.03</b>	<b>1.64</b>	50
including	174.00	188.65	14.65	0.81	0.51	0.02	0.14	0.04	0.05	2.61	50
including	174.00	179.00	5.00	1.21	0.69	0.04	0.14	0.04	0.05	3.32	50
<b>WG-23-038</b>	130.00	140.00	10.00	0.43	0.25	0.01	0.06	0.02	0.21	1.31	75

Hole ID	From (m)	To (m)	Length (m) <sup>1</sup>	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
<b>WG-23-039</b>	<b>191.50</b>	<b>241.00</b>	<b>49.50</b>	<b>0.36</b>	<b>0.28</b>	<b>0.01</b>	<b>0.05</b>	<b>0.02</b>	<b>0.02</b>	<b>1.49</b>	40
including	224.00	241.00	17.00	0.43	0.49	0.01	0.08	0.03	0.04	2.58	40
<b>WG-23-040</b>	<b>169.00</b>	<b>209.00</b>	<b>40.00</b>	<b>0.46</b>	<b>0.32</b>	<b>0.01</b>	<b>0.07</b>	<b>0.02</b>	<b>0.03</b>	<b>1.90</b>	60
<b>WG-23-041</b>	<b>237.00</b>	<b>276.00</b>	<b>39.00</b>	<b>0.43</b>	<b>0.36</b>	<b>0.01</b>	<b>0.17</b>	<b>0.03</b>	<b>0.06</b>	<b>2.04</b>	55
including	243.00	250.00	7.00	0.60	0.49	0.02	0.10	0.03	0.04	2.13	55
including	262.82	275.00	12.20	0.60	0.54	0.02	0.36	0.05	0.11	3.46	55
<b>WG-23-042</b>	<b>256.00</b>	<b>306.00</b>	<b>50.00</b>	<b>1.06</b>	<b>0.34</b>	<b>0.03</b>	<b>0.15</b>	<b>0.04</b>	<b>0.04</b>	<b>1.71</b>	75
including	<b>286.00</b>	<b>306.00</b>	<b>20.00</b>	<b>1.71</b>	<b>0.46</b>	<b>0.05</b>	<b>0.17</b>	<b>0.06</b>	<b>0.06</b>	<b>2.61</b>	75
including	<b>286.90</b>	<b>291.70</b>	<b>4.80</b>	<b>3.15</b>	<b>0.21</b>	<b>0.09</b>	<b>0.15</b>	<b>0.11</b>	<b>0.02</b>	<b>0.95</b>	75
and	331.00	331.40	0.40	6.23	0.30	0.14	0.10	0.12	0.03	2.60	75
and	336.90	337.20	0.30	7.07	0.09	0.15	0.04	0.07	0.01	2.50	75
<b>WG-23-043</b>	<b>212.00</b>	<b>280.00</b>	<b>68.00</b>	<b>0.46</b>	<b>0.36</b>	<b>0.01</b>	<b>0.09</b>	<b>0.02</b>	<b>0.03</b>	<b>1.90</b>	60
including	<b>246.00</b>	<b>280.00</b>	<b>34.00</b>	<b>0.64</b>	<b>0.50</b>	<b>0.02</b>	<b>0.12</b>	<b>0.03</b>	<b>0.04</b>	<b>2.64</b>	60
including	266.00	275.00	9.00	0.94	0.68	0.02	0.19	0.05	0.06	3.83	60
including	277.50	280.00	2.50	0.96	1.02	0.02	0.05	0.04	0.04	4.58	60
and	304.10	304.60	0.50	6.09	0.07	0.12	0.81	0.30	0.03	2.50	60
<b>WG-23-044</b>	362.35	375.40	13.05	0.74	0.81	0.02	0.22	0.05	0.10	4.84	45
including	369.25	375.40	6.15	0.96	1.33	0.03	0.26	0.08	0.18	8.04	45
<b>WG-23-045</b>	286.00	296.00	10.00	0.33	0.24	0.01	0.12	0.02	0.03	1.33	60
and	302.05	304.00	1.95	0.54	0.75	0.02	0.21	0.05	0.11	4.93	60
and	307.55	308.55	1.00	0.81	1.12	0.02	0.31	0.09	0.37	8.50	60
<b>WG-23-046</b>	381.55	402.35	20.80	0.46	0.58	0.01	0.32	0.04	0.14	4.03	65
including	381.55	387.30	5.75	0.51	0.59	0.01	0.76	0.08	0.07	3.79	65
Including	395.30	402.35	7.05	0.89	1.09	0.02	0.29	0.06	0.35	7.63	65
<b>WG-23-047</b>	<b>221.00</b>	<b>271.00</b>	<b>50.00</b>	<b>0.70</b>	<b>0.32</b>	<b>0.02</b>	<b>0.14</b>	<b>0.03</b>	<b>0.04</b>	<b>1.57</b>	80
including	<b>245.00</b>	<b>263.00</b>	<b>18.00</b>	<b>1.27</b>	<b>0.47</b>	<b>0.04</b>	<b>0.20</b>	<b>0.05</b>	<b>0.04</b>	<b>2.16</b>	80
<b>WG-23-048</b>	<b>196.00</b>	<b>229.10</b>	<b>33.10</b>	<b>0.54</b>	<b>0.38</b>	<b>0.02</b>	<b>0.09</b>	<b>0.03</b>	<b>0.03</b>	<b>1.98</b>	85
including	216.00	230.00	14.00	0.76	0.60	0.02	0.14	0.06	0.05	3.03	85
<b>WG-23-049</b>	<b>271.00</b>	<b>302.00</b>	<b>31.00</b>	<b>0.46</b>	<b>0.38</b>	<b>0.01</b>	<b>0.12</b>	<b>0.03</b>	<b>0.04</b>	<b>1.78</b>	70
including	289.00	299.00	10.00	0.69	0.47	0.02	0.16	0.04	0.05	2.10	70
<b>WG-23-050</b>	<b>118.00</b>	<b>143.00</b>	<b>25.00</b>	<b>0.53</b>	<b>0.34</b>	<b>0.02</b>	<b>0.07</b>	<b>0.02</b>	<b>0.03</b>	<b>1.82</b>	85
including	130.00	141.00	11.00	0.76	0.48	0.02	0.10	0.03	0.04	2.56	85
<b>WG-23-051</b>	86.00	111.05	25.05	0.28	0.23	0.01	0.04	0.02	0.02	1.11	100
<b>WG-23-052</b>	<b>174.00</b>	<b>228.00</b>	<b>54.00</b>	<b>0.55</b>	<b>0.29</b>	<b>0.02</b>	<b>0.07</b>	<b>0.02</b>	<b>0.03</b>	<b>1.45</b>	60
including	<b>184.60</b>	<b>208.00</b>	<b>23.40</b>	<b>0.78</b>	<b>0.35</b>	<b>0.02</b>	<b>0.07</b>	<b>0.02</b>	<b>0.02</b>	<b>1.63</b>	60
including	202.50	206.15	3.65	1.24	0.21	0.04	0.11	0.03	0.02	0.92	60
<b>WG-23-053</b>	256.00	259.85	3.85	0.41	0.35	0.01	0.04	0.02	0.02	2.09	90
and	276.75	281.00	4.25	0.49	0.29	0.02	0.08	0.02	0.03	1.62	90
and	294.00	299.00	5.00	0.52	0.35	0.01	0.30	0.06	0.05	2.10	90

Hole ID	From (m)	To (m)	Length (m) <sup>1</sup>	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
<b>WG-23-054</b>	<b>339.00</b>	<b>384.15</b>	<b>45.15</b>	<b>0.38</b>	<b>0.28</b>	<b>0.01</b>	<b>0.18</b>	<b>0.06</b>	<b>0.05</b>	<b>1.74</b>	85
including	348.70	369.00	20.30	0.55	0.38	0.01	0.17	0.04	0.06	2.30	85
<b>WG-23-055</b>	335.00	354.30	19.30	0.36	0.22	0.01	0.09	0.02	0.03	1.00	75
and	382.5	394.00	11.50	0.35	0.25	0.01	0.19	0.03	0.05	0.92	75
<b>WG-23-056</b>	<b>455.00</b>	<b>480.75</b>	<b>25.75</b>	<b>0.47</b>	<b>0.36</b>	<b>0.02</b>	<b>0.15</b>	<b>0.03</b>	<b>0.04</b>	<b>2.01</b>	65
and	485.35	492.00	6.65	0.56	0.46	0.02	0.17	0.04	0.06	2.49	65
<b>WG-23-057</b>	409.00	428.00	19.00	0.41	0.33	0.01	0.09	0.03	0.03	1.67	95
and	447.00	462.00	15.00	0.39	0.28	0.01	0.34	0.07	0.06	0.63	95
and	467.00	468.05	1.05	1.47	0.17	0.04	0.46	0.58	0.09	0.70	95
<b>WG-23-058</b>	327.00	358.00	31.00	0.52	0.37	0.02	0.16	0.03	0.05	2.11	90

**Notes:**

1. Length refers to downhole length. Estimated True Width is expressed as a percentage of downhole length. Bold intervals are based on a Ni wt.% grade thickness greater than 15.